



INSEE Tong

Premium plastering cement
for a perfectly smooth wall.



INSEE TONG

Premium plastering cement
for a perfectly smooth wall.




INSEE Tong is a premium cement which is specially formulated for plastering works :

- Superior cohesiveness and adhesiveness with no sagging and no sift.
- Superior slipperiness and softness with easy mixing.
- Easy spreading and slipperiness with high cohesiveness mortar.
- Fine surface finishing with less cracks, both interior and exterior.
- Can be plastered on clay bricks, concrete blocks and lightweight blocks

With the special admixture pre-added, masons do not need to add any extra admixture during the mixing process thus, supervision time and material cost can be reduced.

Mixing Proportion

Mix the volumetric proportion of **INSEE TONG**, fine sand and water as follows:

Type of work	Mixing Proportion (by Volume)		
	 INSEE TONG	 Fine Sand	 Water
Plastering	1	3	1
Lightweight Block	1	2.2	1

Remark:

- Water content to be adjusted in function of moisture content of sand.

Packaging : 40 kg bag



INSEE TONG is fully compliant to the Quality Standard ASTM C91 Type N and TIS 2595-2013 Type 50 (masonry cement).

Technical Specification		TIS 2595-2556
Blaine	(m ² /kg)	-
Setting Time		
Initial	(min.)	> 120
Final		< 1,000
Standard Mortar Strength		
7 Days	(MPa)	≥ 3.4
28 Days	(MPa)	≥ 6.2

** Updated certification test reports are available upon request.

Recommendations

- Before plastering the wall, clean the surface and moisten the wall to avoid cracks from rapid water absorption.
- Do not directly expose the just finished plastered wall to sunlight to avoid cracks from heat and rapid water loss.
- For plastering works, keep the plastered wall moist during 1-3 days after plastering to avoid cracks and to help the mortar to develop strength.
- Keep the cement dry and under shade, away from the ground, to keep the cement quality.
- Do not store cement for more than 2 months and once opened should be finished within 1-2 day.
- Recommend to wear gloves and long sleeves, to avoid direct contact of cement with the skin.



Contact us

Head office

Siam City Cement Public Company Limited.

Column Tower, 3rd, 10th, 12th Fl.,

199 Ratchadapisek Rd., Klongtoey, Bangkok 10110

Telephone : (662) 797 7000

E-mail : wecare@siamcitycement.com

Customer service center

Website : www.siamcitycement.com

1732